



## **Microbial Degradation of Microplastics in Aquatic Ecosystems: A New Frontier in Environmental Bioremediation**

**Dr. Sneha Khadse**

Department of Research and Academic, Scicarfhub Publication, Mumbai  
 Khadsesneha43@gmail.com

### **Abstract**

Microplastics, which are defined as plastics that are below 5 mm in their dimension, have become widespread pollutants to the marine ecosystem, with dire consequences to marine creatures, ecological balance, as well as human health. The problem of accumulating synthetic polymers has become a burning issue all over the globe due to the recalcitrance nature of these polymers. Microbial degradation has become a trend in recent years as one of the promising environmentally friendly methods to reduce microplastic pollution. Several bacteria, fungi and actinomycetes have shown themselves capable of colonizing, biofilm forming and enzyme degrading polyethylene (PE), polyethylene terephthalate (PET), polypropylene (PP) and polystyrene (PS). In this paper the authors discuss the processes of degradation of microbes, such as enzyme hydrolysis, oxidation, and fragmentation, as well as those environmental conditions that affect the degradation rate. Major microbial genera examined in the study included *Pseudomonas*, *Bacillus*, *Rhodococcus*, *Aspergillus*, and *Ideonella sakaiensis* whose enzymes are PETase and Mhetase, which depolymerize plastics. Besides, the paper also assesses the possibility of using microbial consortia, genetic engineering and bioreactor-based methods to achieve large-scale bioremediation. The findings point to microbial degradation as a potential sustainable, low-cost alternative to physical and chemical degradation, although there are the problems of scalability and rate of degradation. The research arrives at the conclusion that the use of biotechnology and ecosystem-based management to increase microbial activity can help in the world effort to alleviate plastic wastes to a greater extent.

**Keywords:** Microplastics, Biodegradation, Aquatic Microbiology, Environmental Bioremediation, PETase, Plastic Pollution.

### **1. Introduction**

Plastic pollution can now be considered a characteristic environmental problem of the 21st century. About 11 million metric tonnes of plastic waste are deposited into the oceans annually and it is estimated that this number will triple to 110 million metric tonnes by 2040 unless the current trends are reversed (UNEP, 2023). Microplastics, defined as fragments, fibers, and beads of the larger plastic debris or also released directly through the products are now widespread in the marine and freshwater systems (Andrady, 2017). Their resistance and bioaccumulation pose a threat to aquatic food webs, even human health because microplastics have been found in seafood, drinking water, and even atmospheric samples (Ragusa et al., 2021). Physical filtration, incineration, and photodegradation are usual physical methods of mitigation that are either ineffective, expensive or polluting to the environment. Consequently, bio-degradation is gaining more and more interest especially via the metabolic action of microorganisms which can exploit plastics as sources of carbon (Urbanek et al., 2018). Microbial degradation is an environmentally friendly approach, which takes advantage of the metabolic heterogeneity of bacteria and fungi to break down polymers into harmless by-products. This paper discusses microorganisms and their roles in the degradation of microplastics under aquatic conditions, concentrating on enzymatic processes, principal microbial species, the environmental factors and the latest developments in the biotechnology where the degradation rate remains low.




Figure 1. Stages of microbial degradation of microplastics in aquatic ecosystems. Adapted from Urbanek et al. (2018) and Yoshida et al. (2016).

Microbial communities are dual ecologically as they both break down polymers and host horizontal gene transfer and nutrient cycling. With the recent development of genomics and proteomics tools, it is now possible to comprehensively monitor the metabolism of microorganisms during degradation, which can be scaled to biotechnological use.

### Background of the Study

Sources of microplastics can be both primary (e.g., microbeads used in cosmetics) and secondary (i.e. fragmentation of larger plastics under UV radiation, mechanical abrasion, or oxidation). They are highly adsorptive (high surface area) and hydrophobic, which eventually create biofilms that act as microhabitats that host a wide range of microbial communities (known as plastisphere biofilms) (Amaral-Zettler et al., 2020).

Emerging studies perceived plastics as non-biodegradable materials that cannot be attacked by microbes because they contain high molecular weight, are hydrophobic, and their backbones consist of carbon-carbon, which is stable. The identification of plastic-degrading microorganisms, including *Ideonella sakaiensis*, that releases PETase to degrade polyethylene terephthalates (PET) into terephthalic acid and ethylene glycol, however, disagreed with this understanding (Yoshida et al., 2016).

Further research has found a variety of bacterial genera (*Pseudomonas*, *Bacillus*, *Rhodococcus*) and fungi (*Aspergillus*, *Penicillium*) that could grow on and break plastic polymers in aquatic environments (Ojha et al., 2017). These microbes use oxidative, hydrolytic, and enzymatic processes to break down plastics into oligomers and monomers and then CO<sub>2</sub> and H<sub>2</sub>O.

The new microbial bioremediation of microplastics is therefore an area of convergence between environmental microbiology and biotechnology on the one hand, and sustainability science on the other.

### Justification

The presence of microplastics in the aquatic systems has multidimensional risks: ecological disbalance, bioaccumulation in the food chain, and the possible harmful risks to human health. The chemical and mechanical remedial techniques consume energy, which cannot be used at large scale and it produces other pollutants. Microbial degradation offers a cost-effective, natural and sustainable solution. It is necessary to learn the diversity, enzymatic dynamics, and ecological activity of plastic-degrading microbes, to develop biotechnological solutions such as bioaugmentation, enzyme engineering, and the implementation of microbial consortia (Urbanek et al., 2018). The necessity to implement innovative and environmentally friendly approaches that support the UN Sustainable Development Goals (SDGs) in the form of SDG 14 (Life Below Water) and SDG 12 (Responsible Consumption and Production) justifies this study.

### 4. Objectives of the Study

The overall objectives of the current research are to:

- People study microbial species that are involved in the degradation of microplastics in water.
- Describe microbial degradation biochemical and enzymatic pathways.
- Establish the physical and environmental conditions, which influence the degradation rates.
- Convert the potential of microbial consortia and biotechnological in large scale bioremediation.

## Literature Review

This theory argues that, based on the degradation process of plastics microbial diversity also changes over time (Bhatia 171).

It is also discovered that a broad diversity of taxa of microbes is capable of growing and degrading plastic surfaces. Extracellular enzymes have been found to oxidize polyethylene (PE) and polypropylene (PP) by *Pseudomonas aeruginosa*, *Rhodococcus ruber* and *Bacillus subtilis* (Sivan, 2011). Fungi that are used to degrade PET and polystyrene (PS) using oxidative enzymes, laccases, and esterases include *Aspergillus niger* and *Penicillium chrysogenum* (Kale et al., 2015).

## 5.2 Enzymatic Mechanisms

The enzymes that are involved in the microbial degradation include some of the PETase, MHETase, laccases, peroxidases, and cutinases. PETase was first identified in *I. sakaiensis* and cleaves down PET to monomers and MHETase monomeric byproducts to ethylene glycol and terephthalic acid (Yoshida et al., 2016). Similarly, *Pseudomonas* and *Rhodococcal* strains secrete oxidases and hydrolases that result into surface oxidation, increase the hydrophilicity of polymers and permit enzyme attacks.

## 5.3 Environmental Factors

Temperature, salinity, pH and UV exposure play a very important role in microbial degradation. The maximum rate of degradation is normally optimized at mesophilic temperatures (25-37 °C) and at neutral pH but certain halophilic or psychrophilic organisms have adapted to survive under harsh conditions in water (Shah et al., 2008).

## 5.4 Biofilm Formation and Ecology of Plastisphere

The microplastics that are colonized by microbes lead to the development of biofilms, the plastisphere (Amaral-Zettler et al., 2020). These biofilms also influence the nutrient cycle and pollutant transportation in the water bodies, in addition to leading to degradation.

The advances in genetic and synthetic biology encompass the advances in synthetic biology, which is the process of developing systems or devices that utilize biochemical reactions (including enzyme catalysis or ionic transport) as their inputs and outputs controlled by outside forces. The advances in synthetic biology are enhancements in the field of synthetic biology, which is the creation of systems or devices to be capable of externally manipulating biochemical reactions (enzymatic catalysis, ionic transport). The recent advances in biotechnology have aided in engineering of enzymes to make them degrade more. The catalytic efficiency of mutant PETase copies is up to 3-fold (Tournier et al., 2020). It is recommended that bioremediation of aquatic environment is scaled up in terms of synthetic microbial consortia and bioreactors.

## Material and Methodology

This paper will rely on the systematic review methodology, whereby the secondary information will be gathered in the form of peer-reviewed journals, institutional reports (UNEP, 2023; OECD, 2022), and latest meta-analyses of microbial degradation of plastics.

The database databases such as Scopus, PubMed, and ScienceDirect were searched using keywords such as microbial degradation, microplastics, PETase, aquatic bioremediation and plastisphere ecology.

### Inclusion criteria:

- Publications between 2010–2024;
- Studies that showed evidence of microbial degradation rate, enzyme activity or polymer degradation evidence;
- Ecological, initiate aquatic environments.
- Synthesis of data was done in terms of thematic categories i.e. microbial taxa, degradation mechanisms, environmental influences, and biotechnological innovations.

## 7. Results and Discussion

**Table 1. Representative Microorganisms Involved in Plastic Degradation**


Microorganism	Polymer Degraded	Key Enzyme(s)	Habitat Type	Reference
<i>Ideonella sakaiensis</i>	PET	PETase, MHETase	Freshwater sediment	Yoshida et al., 2016
<i>Pseudomonas</i>	PE, PS	Laccase, Esterase	Marine biofilm	Sivan, 2011

Microorganism	Polymer Degraded	Key Enzyme(s)	Habitat Type	Reference
<i>aeruginosa</i>				
<i>Rhodococcus ruber</i>	PE	Alkane hydroxylase	Estuarine water	Urbanek et al., 2018
<i>Aspergillus niger</i>	PET, PP	Cutinase, Peroxidase	Brackish water	Kale et al., 2015
<i>Bacillus subtilis</i>	PE	Oxidase, Protease	River sediment	Ojha et al., 2017

**Table 2. Comparison of Biodegradation Rates of Plastics by Selected Microbes**

Polymer Type	Microorganism	Degradation Rate (% Weight Loss)	Incubation Period (Days)	Environmental Condition
PET	<i>I. sakaiensis</i>	20–25%	60	Neutral pH, 30°C
PE	<i>P. aeruginosa</i>	15%	90	Marine, 28°C
PP	<i>A. niger</i>	12%	75	Mesophilic, 32°C
PS	<i>R. ruber</i>	10%	60	Estuarine, 30°C

**Note.** Data adapted from Yoshida et al. (2016), Urbanek et al. (2018), and Kale et al. (2015).

**Figure 1. Selecting microorganisms to degrade plastic: Efficiency of different microorganisms in four types of polymers**

Bar chart of percentage degradation of PET, PE, PP, and PS by five microorganisms Ideonella sakaiensis, Pseudomonas aeruginosa, Rhodococcus ruber, Aspergillus niger, and Bacillus subtilis. Ideonella sakaiensis was the most active (25) degrading PET with insignificant activity on other polymers. The polymers PE and PP were mainly degraded by Rhodococcus ruber and Pseudomonas aeruginosa and moderately by Aspergillus niger and Bacillus subtilis. There are color-coded bars that depict the types of polymers.

### Limitations of the Study

- The review is based on secondary literature; quantitative comparisons of studies cannot be based on direct methods because of methodological diversity.
- Laboratory degradation conditions could be unrealistic of natural aquatic environments.
- Inability to have long-term field tests of engineered enzymes or consortia.
- Poor knowledge on ecological side effects of microbial bioaugmentation.

### Future Scope

The future studies must be based on:

- Plastisphere profiling of different aquatic ecosystems.
- High efficiency enzyme genetic engineering (e.g. PETase mutants).
- Synthetic consortia design to degrade mixed polymers.
- Bioreactor design to microplastic bioremediation on a large scale.
- Environmental application: ecotoxicology of microbial-degraded by-products.

## Conclusion

The microbial degradation is one of the promising spheres of the fight against microplastic pollution in aquatic environments. The heterogeneity of plastic-degrading microbes, combined with the progress in the field of enzymology and biotechnology, provides the alternative to traditional remediation methods as one that is sustainable. Despite the current problems with scalability and lack of ecological safety, strategic combination of microbial biotechnology, synthetic biology, and environmental regulation may reinvent the world perception of managing aquatic pollution.

## References

1. Amaral-Zettler, L. A., Zettler, E. R., & Mincer, T. J. (2020). Ecology of the plastisphere. *Nature Reviews Microbiology*, 18(3), 139–151.
2. Andrady, A. L. (2017). The plastic in microplastic pollution: A perspective on the science and the challenges. *Marine Pollution Bulletin*, 119(1), 12–22.
3. Kale, S. K., Deshmukh, A. G., & Patil, V. B. (2015). Microbial degradation of plastic: A review. *Journal of Biochemical Technology*, 6(2), 952–961.
4. Ojha, N., Pradhan, N., Singh, S., et al. (2017). Evaluation of HDPE degradation by *Bacillus subtilis*. *3 Biotech*, 7(1), 73–81.
5. Ragusa, A., Svelato, A., Santacroce, C., et al. (2021). Plasticenta: First evidence of microplastics in human placenta. *Environment International*, 146, 106274.
6. Shah, A. A., Hasan, F., Hameed, A., & Ahmed, S. (2008). Biological degradation of plastics: A comprehensive review. *Biotechnology Advances*, 26(3), 246–265.
7. Sivan, A. (2011). New perspectives in plastic biodegradation. *Current Opinion in Biotechnology*, 22(3), 422–426.
8. Tournier, V., Topham, C. M., Gilles, A., et al. (2020). An engineered PET depolymerase to break down and recycle plastic bottles. *Nature*, 580(7802), 216–219.
9. UNEP. (2023). *Turning off the tap: How the world can end plastic pollution*. United Nations Environment Programme.
10. Urbanek, A. K., Rymowicz, W., & Strzelecki, M. (2018). Degradation of plastics by filamentous fungi. *Applied Microbiology and Biotechnology*, 102(16), 6513–6529.
11. Yoshida, S., Hiraga, K., Takehana, T., et al. (2016). A bacterium that degrades and assimilates poly(ethylene terephthalate). *Science*, 351(6278), 1196–1199.